

## Slip Check to AS 4586-2013 Pantora Laminate Amor Collection

**Report Number: R33561**

**Report Date: 1 April 2025**

**Total Number of Pages 2**

Safe Environments quality management system is certified to ISO 9001:2015

Accredited for compliance with ISO/IEC 17025 – Testing

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration, inspection, proficiency testing scheme providers and reference materials producers reports and certificates

**Issued by**

Safe Environments Pty Limited  
6/7 Inglewood Place  
Norwest NSW 2153

**Prepared for**

Topdeck Flooring  
16 Salisbury Street  
Silverwater NSW 2128

**Approved by**

  
Ratan Venkatesan  
Authorised Signatory

1 April 2025

# Test Report No. R33561

## Slip Resistance Classification of New Pedestrian Surface Materials

AS 4586-2013 Appendix A (Wet Pendulum Test)

The slip resistance classification has been determined for unused surfaces under specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface after classification. Standards Australia Handbook 198:2014 *Guide to the specification and testing of slip resistance of pedestrian surfaces* provides guidance for the selection of slip resistant pedestrian surfaces classified in accordance with AS 4586-2013. It is recommended that this test report be read in conjunction with AS 4586, HB 197 & HB 198.

Requested by: Topdeck Flooring  
Client Address: 16 Salisbury Street  
Silverwater NSW 2128  
Product Manufacturer: Supplied by Topdeck Flooring  
Product Description: Pantora Laminate Amor Collection

Test conducted according to: AS 4586:2013 Appendix A  
Sampling Procedures: Performed by client and tested as received.  
Location: 6/7 Inglewood Place, Norwest NSW 2153

Conducted by: Nathan Vanderburg

Date: 01 April 2025  
Sample: Unfixed  
Rubber slider used: Slider 96  
Slope of specimen: Tested on a flat level surface  
Direction of Test: With grain  
Temperature: 23°C  
Cleaning: None  
Conditioned: Grade P 400 paper dry followed by wet lapping film

	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Mean BPN of last 3 swings:	36	35	34	36	38

<b>Reported SRV of Sample:</b>	<b>36</b>
<b>Class:</b>	<b>P3</b>

The expanded uncertainty ( $U_{95}$ ) at the 95% level of confidence with a coverage factor ( $k$ ) of 2 has been estimated to be 3 BPN or 8 %, whichever is the greater; sampling uncertainty has not been included. The expanded uncertainty should be considered when interpreting results or assessing conformity. Results relate only to items tested.