

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Topdeck International Pty Ltd
16 Salisbury Street
Silverwater NSW 2128

Test Number : 17-000094
Issue Date : 24/01/2017
Print Date : 24/01/2017

Sample Description Clients Ref : "Endurance Engineered Bamboo Flooring"
Engineered Floorboards
Colour : Natural
End Use : Flooring
Nominal Composition : Bamboo Veneer over plywood base
Nominal Mass per Unit Area/Density : 750kg/m³
Nominal Thickness : 14mm

AS/ISO 9239.1-2003

Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source

Date of Sample Arrival 16/01/2017
Date Tested 24/01/2017

CHF Value	1	2	3	Mean
Length	3.7	4.2	3.4	3.8 kW/m ²
Width	6.4	-	-	- kW/m ²

Smoke Value	1	2	3	Mean
Length	6	6	9	7 %.min
Width	50	-	-	- %.min

Blistering	Yes
Glowing	Yes
Smouldering	Yes

81022

16954

Page 1 of 2

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025
- Chemical Testing
- Mechanical Testing
985

: Accreditation No.
: Accreditation No.

983

Samples and their identifying descriptions have been provided by the client unless otherwise stated.
AWTA
Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall



AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Topdeck International Pty Ltd
16 Salisbury Street
Silverwater NSW 2128

Test Number : 17-000094
Issue Date : 24/01/2017
Print Date : 24/01/2017

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2001 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Each specimen was clamped to a substrate of 6mm thick fibre reinforced cement board prior to testing.

81022

16954

Page 2 of 2

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025
- Chemical Testing
- Mechanical Testing
985

: Accreditation No.
: Accreditation No.

983

Samples and their identifying descriptions have been provided by the client unless otherwise stated.
AWTA
Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall



APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR